

### BLUE MEDIUM STRENGTH THREADLOCKER MEDIUM VISCOSITY PART NO. 49442

#### PHYSICAL PROPERTIES

##### Monomer (Liquid)

Base Compound .....	Dimethacrylate Ester
Color .....	Blue
Viscosity (cP @ 68°F) .....	1000 cP
Flash Point (TCC) .....	>200°F
Gap Fill .....	.007"
Corrosivity .....	None
Toxicity .....	Low
Specific Gravity (g/cc) .....	1.1
Shelf Life @ 40°F .....	1 year unopened
Military Specifications .....	Mil-S-46163A
	Type II Grade N
Curing Properties .....	Depends on environmental conditions and the substrates used

##### Polymer (Cured)

Locking Strength .....	Medium
Service Temperature Range .....	-75°F to 300°F
Appearance .....	Blue liquid
Shear Strength (steel nuts and bolts) .....	1200 psi
Full Cure Time .....	24 hours



#### DESCRIPTION

**Dynatex® Blue Medium Strength Threadlocker** is a medium strength anaerobic threadlocking material, which cures between engaged threads to form a unitized assembly that resists virtually all leakage, shock and vibration. The product is a single component, anaerobic liquid that cures when confined in the absence of air between close fitting metal surfaces. Ideal for all ¼ inch to ¾ inch diameter nut and bolt assemblies. Fills gaps up to .006 inches. Applied prior to assembly. Eliminates need for stocking lock nuts and lock washers. Excellent chemical resistance with a temperature resistance range of -65°F to 350°F (-54°C to 177°C). Easily removable with hand tools for servicing requirements. Protects against thread corrosion.

#### FEATURES

- No mixing
- No curing outside of joint
- Eliminates vibration issues
- Seals against leakage
- Can be adjusted or disassembled
- Cures without cracking or shrinking
- Prevents rusting of threads
- No torque compensation required during assembly

#### TYPICAL APPLICATIONS

- Cup and core plugs
- Starter mounting bolts
- Alternator mounting bolts
- Oil pan bolts
- Intake manifold bolts
- Drive shaft bolts
- Pulley bolts
- Valve cover bolts and more.....

## PERFORMANCE OF CURED MATERIALS

Bond strength after 24 hours at 20°C to 25°C  
on steel nuts and bolts

	Average Value	Range
Breakaway Torque	125 in. lbs.	100-150 in. lbs.
Prevailing Torque	70 in. lbs.	35-100 in. lbs.

## CURING PERFORMANCE

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

## SETTING TIME (68°F, 65% R.H.)

Substrate	Set time/Full cure
Steel	10 min/24 hrs
Brass	15 min/24 hrs
Zn Dichromate	20 min/24 hrs
Stainless Steel	20 min/24 hrs

## CHEMICAL RESISTANCE

Shear strength on steel after 500 hours.

Solvent	% Strength Retained
Motor Oil	100
Unleaded Gasoline	100
Trichloroethane	100
Brake Fluid	100
Ethanol	100
Acetone	100
Water/Glycol Mix	80

## GENERAL INSTRUCTIONS

Surfaces to be bonded should be clean and dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps, which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

**This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® Blue Medium Strength Threadlocker** has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Non-warranty:** Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted. Suggestions of uses should not be taken as inducements to infringe any patents.

**Dynatex®** A division of Accumetric, LLC

**Dynatex**  
350 Ring Road  
Elizabethtown  
Kentucky 42701 USA  
(800) 999-2937  
TEL (270) 769-5557  
FAX (270) 769-6418  
Outside U.S.  
TEL +1(270) 769-5557  
FAX +1(270) 769-6418

**Accumetric Asia Pacific, LTD**  
18 Kitpanit Bldg. 5<sup>th</sup> Floor  
#502 Patpong Road  
Suriyawong, Bangrak  
Bangkok, 10500 Thailand  
TEL (662) 634-3060  
FAX (662) 634-3066

Email: sales@dynatexinc.com  
Website: www.dynatexinc.com