Soudafoam Gap Fill



- High Expanding Gun Foam
- Excellent Filling Characteristics
- Excellent Adhesion to All Building Materials (except PE, PP and PTFE)
- Very High Insulation Values, Both Thermal and Acoustical
- Easy Application
- Excellent Form Stability No Shrink, No Post Expansion
- No Shrinkage
- CFC Propellants Free Harmless to Ozone Layer



Filling of Cavities Seals Openings & Gaps Creates Acoustic Screen

This information and all further technical advice are based on SOUDAL present knowledge and experience. However, SOUDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SOUDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOUDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOUDAL reserves the right to make any changes according to technological progress or further developments.

Soudafoam Gap Fill



Base	Polyurethane
Consistency	Stable foam (does not sag)
Curing system	Moisture-cure
Skin Formation (68°F at 60% R.H.)	Approx. 10 minutes
Drying time	Approx. 90min - 1.2 inch foam bead (68°F/65% R.H.)
Curing rate (68°F/65% R.H.)	1 hour for a 1/8" bead
Shrink	<7%
Post expansion	None
Cellular structure	Ca 70-80% closed cells
Specific gravity	Ca. 1.62lb/ft³ (extruded, fully cured)
Temperature resistance	-40°F until +194°F when cured Short term (up to 1 hour) 248°F
Color	Champagne
Fire Class	B3 (DIN4102 part2)
Water Absorption	1% Vol. (DIN53422)
Insulation Factor: R-value	4.0 for 1 inch
Pressure Strength	Ca. 4.3 psi
Bowing Strength	Ca. 8.6 psi
Shear Strength	Ca. 20psi

(*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Limitations:

- Excellent adhesion on most substrates, except for PTFE, PE and PP.
- Always store can with the valve pointed upwards.
- Cured PU foam must be protected from UV radiation.
- Lower temperature and humidity will extend curing time.

CAUTION

KEEP OUT OF REACH OF CHILDREN. For professional use only. KEEP AWAY FROM HEAT (>40°F), SPARKS AND OPEN FLAME. DO NOT PUNCTURE OR INCINERATE CAN. DO NOT EXPOSE TO DIRECT SUNLIGHT. USE ONLY IN WELL VENTILATED AREAS. In case of eye contact, flush eye with water for 15 minutes and get immediate medical attention. For inhalation, move to fresh air. For skin contact, wash thoroughly with water and soap. If swallowed, drink large quantities of water, but do not induce vomiting. Call a physician immediately. Refer to SDS for further information.

PLEASE REFER TO TECHNICAL DATA SHEET FOR COMPLETE INFORMATION ABOUT THE PRODUCT

